

**Research Article****Removal of Lead (II) Ion from Aqueous Solution by Adsorption unto Chitosan Polymer**

Anduang Ofuo Odiongenyi**Department of Chemistry, Akwa Ibom State University
Ikot Akpaden, Mkpato Enin LGA, Akwa Ibom State, Nigeria****Email: anduangodiong@gmail.com**

Abstract

The adsorption efficiency of chitosan for Pb^{2+} ion was investigated for various concentrations of the metal ion solution at different time and at various temperatures. The Chitosan displayed good adsorption properties of the metal ion. FTIR study revealed that the major shifts in the frequencies of adsorption. New bonds were formed at 1411, 2262 and 3759 cm^{-1} while N-H and C-O bond at 1587 and 1320 cm^{-1} respectively. The new and missing bonds were assumed to be directly involved in the absorption of lead ion onto chitosan surface.

Key Words: Heavy metal pollution, lead ion, remediation, adsorption, chitosan.

Received: 24/04/18

Accepted: 29/06/18

Introduction

Water pollution is an endemic problem because it is generated at a source (where wastes are discharged) but widely transported to several locations and has the potential of affecting the entire ecosystem. Industrialization is the earnest expectation of a developed and developing nation. However, industrialization releases several pollutants to the environment, which implies that the discharge of waste should be properly monitored. A cardinal point in waste disposal is to reduce the toxic components of a given waste to permissible value. Heavy metals are common industrial

This work is licensed under a [Creative Commons Attribution 4.0 Unported License](https://creativecommons.org/licenses/by/4.0/)
ISSN: 1597 – 9928 Science and Education Development Inst., Nigeria

waste and their disposal to water bodies can affect the quality of the water, aquatic animal and even man through bioaccumulation.

Adsorption is one of the most effective methods available for the removal of heavy metals from aqueous solution. Adsorption involves the use of suitable adsorbent through which the metal ion will be adsorbed onto the surface by physiosorption or chemisorptions mechanism. Several adsorbents have been reportedly used for the removal of heavy metals from aqueous solution but some of the adsorbents are less effective, some are non-biodegradable while other are expensive. The present study is aimed at using chitosan to remove lead (II) ion from aqueous solution. The application of biopolymers such as chitin and chitosan is one of the emerging adsorption methods for the removal of heavy metal ions, even at low concentrations (Crini, 2006). Chitosan is a natural polyaminosaccharide, synthesized from the deacetylation of chitin, a polysaccharide consisting predominantly of unbranched chains of $-(1\rightarrow4)-2$ -acetoamido-2-deoxy-d-glucose. Chitin is the second most abundant polymer in nature after cellulose. It can be extracted from crustacean shell such as prawns, crabs, fungi, insects and other crustaceans Wan *et al.*, (2000). It is an established fact that chitosan exhibits natural support for enzyme immobilization because of its special characteristics such as hydrophilicity, biocompatibility, biodegradability, non-toxicity, adsorption properties, etc (Kumar, 2000). Chitosan can be used as an adsorbent to remove heavy metals and dyes due to the presence of amino and hydroxyl groups which are active functional groups for adsorption (Wu *et al.*, 2001). The chemical structure of chitosan is shown in Fig 1.




Fig 1: Chemical structure of chitosan

Several works on adsorption of heavy metals using chitosan or modified chitosan polymers have been reported. Some of them are graft copolymerization of polyacrylonitrile on the chitosan surface in the presence of ceric ammonium for the removal of Cr (VI) and Cu (II) ions from aqueous media (Shanmugapriya *et al.*, 2013). Thiourea modified chitosan for the adsorption of Hg (II) (Hritcu *et al.*, 2012). Beads of

This work is licensed under a [Creative Commons Attribution 4.0 Unported License](https://creativecommons.org/licenses/by/4.0/)
ISSN: 1597 - 9928 Science and Education Development Inst., Nigeria

thiourea-modified chitosan used for the adsorption of Cu (II) was prepared by several media (citric acid, sodium hypophosphite, glutaraldehyde, and SiO₂) (Benavente *et al.*, 2011). Graft copolymerization of chitosan with polyacrylonitrile in the presence of ceric ammonium nitrate used for the removal of Pb (II) and Ni (II) ions from aqueous solutions (Repo *et al.*, 2011). In order to facilitate the adsorption efficiency, Shanmugapriya *et al.* (2011) combined chitosan with sodium alginate for the removal of Cu (II), Cd (II), Pb (II) and Ag (II) ions from waste water.

The Cu (II) and Ni (II) ions were removed from metal solution by using crosslinked chitosan synthesized by graft copolymerization of chitosan with acrylonitrile in presence of ceric ammonium nitrate as initiator. Adsorption of Lead (II) ion on chitosan has found to be dependent on contact time, concentration, temperature, and pH of the solution (Chiou *et al.*, 2004; Wu *et al.*, 2001).

The aim of the study was to investigate the adsorption efficiency of chitosan for Pb²⁺ ion at various concentrations of the metal ion solution at different time and at various temperatures.

Materials and methods

Chitosan sample was supplied by Prof. Lee Wills, a Professor in the Department of Chemistry, University of Saskatchewan, Canada. Batch experiments were carried out as reported elsewhere to investigate the effect of concentration on the adsorption of various concentrations of lead by chitosan. The wavelength of maximum absorption of lead was determined using Pye Unicam Atomic Absorption Spectrophotometer and this wavelength was used for subsequent analysis after the preparation of calibration curve. Concentration of lead adsorbed was calculated using the following equation, FTIR analysis of the samples (chitosan before and after adsorption of lead ion) was carried out using FTIR spectrophotometer. The samples were prepared using KBr powder and the scanning was done in the range of 450 to 500 cm.

Results and Discussions

Adsorbance study

The adsorption of lead ion from aqueous solution has been found to depend on a number of factors, including period of contact, pH, temperature, mass of the adsorbent, concentration of the adsorbate, particle size, etc. However, in this work, the only effect of temperature, contact time and concentration of adsorbate was investigated.

This work is licensed under a [Creative Commons Attribution 4.0 Unported License](https://creativecommons.org/licenses/by/4.0/)
ISSN: 1597 - 9928 Science and Education Development Inst., Nigeria

Spectrophotometric method was used for analysis of the solution containing unadsorbed lead ions. The implication is that the difference in adsorbance before and after adsorption is an indication of the amount of lead ion that is adsorbed. This is because, according to Beer-Lambert law, absorbance is directly proportional to concentration, ie,

$$A = \epsilon l C \quad 1$$

Where A is the adsorbance, l is the path length of the sample cuvette (which is constant) and C is the concentration of the analyte. The mathematical significance of the equation is that a plot of A versus C should give a straight line passing through the origin, whose slope is equal to ϵ , the molar absorptivity (since in most cases l is always equal to unity). From the above, it is conventional that the adsorbance of the solution containing unadsorbed lead ions will decrease as the concentration of lead ion adsorbed increases and vice versa. Therefore, this study presents a preliminary method for evaluating the extent of adsorption of lead ions on chitosan at various temperature, time and concentration. Fig. 2 shows plots for the variation of adsorbance with concentration for solution containing various concentrations of lead ions.




Fig. 2: Variation of adsorbance with initial concentration of Pb^{2+}

The adsorbance is seen to decrease with increase in concentration indicating that the concentration of lead ion unadsorbed decreases as the concentration of adsorbed lead ion increases. Increase in the amount of heavy metal ion adsorbed with concentration is an indication that the adsorption process is effective. As the concentration of the solution increases, the amount of lead ion in the solution increase, the probability of sticking also increases hence the Observe trend.

In order to investigate the effect of time on the adsorption of Pb^{2+} by chitosan, adsorbance of 500 ppm solution of the heavy metal ion (in contact with the adsorbent at various time) were measured. The data obtained were used to develop the plot given in Fig. 2.

The graphs reveal that the adsorbance first increases and then decreases with time. The initial increases correspond to the point where the amount of Pb^{2+} adsorbed is minimum while the progressive decreases indicate that the amount of lead ion adsorbed increases with time. An increase in the amount of adsorbate with time is due to the fact that as the period of contact increases, the tendencies of the adsorbate to be adsorbed increases until all the vacant adsorption sites are completely covered. The results obtained suggest that the best adsorption efficiency of chitosan for Pb^{2+} will be time dependent. Therefore, optimum performance of chitosan as an adsorbent for lead ion can be achieved by taking advantage of background factors, including time.

Fig. 3 shows a plot for the variation of adsorbance of solution containing unadsorbed lead ion with temperature. The plot reveals that the adsorbance of the solution decreases with temperature. This implies that as the temperature increases, the amount of lead ion adsorbed by chitosan also increases. The observed trend suggests that the adsorption of lead ion on the surface of chitosan is consistent with the mechanism of chemical adsorption. In chemical adsorption, the extent of adsorption increases with increase in temperature, whereas in physical adsorption, the extent of adsorption decreases with increase in temperature.




Fig. 3: Variation of absorbance of solution of unadsorbed Pb^{2+} with concentration

Temperature can exert several significant impacts on the surface properties of an adsorbent. At high temperature, the adsorbent may be activated, charged or modified in such a manner that the number of adsorption site increases or become more active. Temperature can also modify some functional groups in the chitosan and encourage better adsorption.




Fig. 4: variation of adsorbance of solution of unadsorbed Pb^{2+} with temperature

FTIR study

Fig. 4 shows the FTIR of pure chitosan while the peaks and the frequency of adsorption are shown in Table 1. From the results obtained, the main functional groups or vibrations associated with chitosan are the C-N stretch at 1082 cm^{-1} , N-H bending vibration at 1587 cm^{-1} , C=C stretch at 1649 cm^{-1} , C-H stretch at 2890 cm^{-1} and OH stretch at 3385 cm^{-1} . After adsorption of lead ion by chitosan, the spectrum obtained is shown in Fig. 5 and 6 while the peaks and frequencies of adsorption are recorded in Table 2.

C-N stretch shifted from 1082 to 1040 cm^{-1} with increase intensity and increasing area. C=C stretch shifted from 1649 to 1547 cm^{-1} , C-H stretch at 2890 shifted to 2903 cm^{-1} and OH stretch at 3385 shifted to 3422 cm^{-1} . New bonds were formed at 1411 , 2262 and 3759 cm^{-1} while N-H and C-O bond at 1587 and 1320 cm^{-1} respectively, were missing. Interestingly, the shift between 1082 and 1649 cm^{-1} occurred with increasing intensity suggesting better bond compartment through adsorption. Generally, shift in frequency after adsorption agrees with the existence of interaction between the adsorbent (chitosan) and the adsorbate (lead ion) while the appearing of new bond suggests the point of adsorption facilitated by the missing bond.




Fig. 5: FTIR of chitosan

Table 1: Frequencies and peaks of FTIR spectrum of chitosan

Frequency	Intensity	Area	Assignment	
1082	17	276	C-N stretch	Amine
1320	21	76	C-O stretch	Alcohol, carboxylic acid, ether, ester
1587	21	54	N-H bend	Amine
649	20	133	C=C	Alkene
2890	19	387	C-H stretch	Alkane
3385	15	253	OH stretch	Alcohol, phenol




Fig. 6: FTIR of chitosan after adsorption of Pb^{2+}

Table 2: Frequencies and peaks of FTIR spectrum of chitosan after adsorption of Pb^{2+}

Frequency	Intensity	Area	Assignment
577	43	142	C-X stretch Alkyl halide
1040	34	150	C-N stretch Amine
1411	45	63	
1642	44	101	C=C Alkene
2014	49	60	
2262	49	81	
2903	41	231	C-H stretch Alkane
3422	36	122	OH stretch Alcohol, phenol
3759	44	25	

Conclusion

The results and findings obtained from the study on the removal of lead ion from aqueous solution, leads to the following conclusions;

- i. Chitosan is a good adsorbent for Lead ion from aqueous solution.
- ii. The adsorption capacity of chitosan for lead ion increases with increase in concentration.
- iii. The adsorption capacity of chitosan for lead ion increase with increase in temperature, which suggest the mechanism of chemical adsorption.
- iv. The adsorption of lead ion on chitosan can be optimized for better efficiency by taking advantage of time, concentration and temperature.

Acknowledgement

The author is grateful to Prof Williams Lee and Prof. Nnabuk Okon Eddy, who provided the chitosan sample for the study.

References

- Adelaja O. A, Amoo I.A, Aderibigbe A.D. (2011). Biosorption of Lead (II) ions from aqueous solution using *Moringa oleifera* pods, *Scholars Research Library Archives of Applied Science Research*.
- Adeyemi, A.F, Oluyemi E.A, Olabanji I.O., (2012). Removal of Pb^{2+} and Cd^{2+} ions from wastewaters using palm kernel shell charcoal. *Research Journal in Engineering and Applied Sciences*. 308-313.
- Babel S. and Kurniawan T.A., (2003). Low-cost Adsorbents for Heavy Metals uptake from contaminated water: A Review of Hazard Mater, 97,219-243.
- Benavente, M., Moreno, L. And Martinez, J. (2011). Sorption of Heavy Metals from Gold Mining Wastewater using Chitosan. *J. Taiwan Inst. Chem. Eng.* **42** (6) 976-988.
- Bhasin, K., (1991). Participatory Development Demands Participatory Training. *A Journal of Adult Educational Development*. Vol.36: 3-21.

Chen, J. Paul And Minsheng Lin (2001).Equilibrium and Kinetics of Metal ion Adsorption onto a commercial h-type granular activated Carbon: Experimental and modeling studies". *Journal of the International Water Association*. 35, 2385-2394.

Chiou, M. S., Ho, P. Y. and Li H Y. (2004). Adsorption of anionic dyes in acid solutions using chemically cross-linked chitosan beads. *Dye Pigment*. 60(1):69-84.

Chris a. Christophi and Lisa Axe (2000). *Competition of Cd, Cu, and Pb adsorption on goethite*". *Journal of Environmental Engineering*. 126 (1):66-74.

Corapcioglu M.O. and Huang C.P. (2006).The Adsorption of Heavy Metals onto Hydrous Activated Carbon. *Water Research*. 21(9) 1031-1044.

Crini, G. And Badot, P. M. (2008). Application of Chitosan, a Natural Aminopolysaccharide, for dye removal from aqueous solutions by adsorption processes using batch studies: A Review of recent Literature. *Progress in Polymer Science* 33(4):399-447.

Dhanesh, S., Mishra, M., Mishra, A. K. And Anjali, S.(2013). Removal of Lead from waste water using low cost adsorbent. *International Research Journal of Environment Sciences* 2(9):23-26.

Eddy, N. O. (2009). Modeling of the adsorption of zn^{2+} from aqueous solution by modified and sun modified *Cyperus esculentus* shell. *Electronic Journal of Environmental, Agriculture & Food Chemistry*. 8 (11),1177-1185.

Eneh, O.C., (2011a). Crippling Poverty amidst Corporate Social Actions: A Critique of Peripheral Corporate Community Involvement In The Niger Delta Region Of Nigeria. *Asian J. Rural Devel.*, 1:1-20. Crossref , Retrieved from direct link.

Eneh, O.C.,(2011b). Enhancing Africa's Environmental Management: Integrated Pest Management for the Minimization of Agricultural Pesticides Pollution. *J. Environ.* Retrieved from <http://www.scsi.Technol10.3923/rjes.2011>.

Eneh, O.C.(2011c). Failed Development Vision, Political Leadership And Nigeria's Underdevelopment:Acritique.*Asianj.Ruraldev.*,1:63-69.crossref | directlink | eneh, o.c.,

2011. Managing Nigeria's Environment: The Unresolved Issues. *J. Environ.* Retrieved from <http://www.scsi.Technol10.3923/rjes.2011>.

Hastuti, B And Siswanta, D. (2013). The synthesis of carboxymethyl chitosan-pectin film as adsorbent for lead (ii) metal. *International Journal of Chemical Engineering and Applications*. 4(6):349-353.

Hritcu, D., Dodi, Ga And Popa, M. I. (2012). Heavy Metal Ions Adsorption on Chitosan-Magnetite Microspheres. *International Review of Chemical Engineering*. 4:364-368.

Islam, S., Shahid, M and Mohammad, F. (2013). Green Chemistry Approaches to Develop Antimicrobial Textiles Based on Sustainable Biopolymers-a Review. *Industrial Engineering Chemistry Research*. 52 (15): 5245-5260.

Jayakumar R, Menon D, Manzoor K, Nair Sv, Tamura H.,(2010). Biomedical Applications of Chitin and Chitosan Based Nanomaterials, a Short Review. *Carbohydr Polym* 82(2):227-232.

Jimoh T.O. (2012). Utilization of *Blighia sapida* (Akee Apple) Pod In The Removal of Lead, Cadmium and Cobalt Ions From Aqueous Solution, *Journal Of Environmental Chemistry and Ecotoxicology*. 4(10):178-187.

Kadirvelu, K (2002). Adsorption of Lead (ii) From Aqueous Solution By Activated Carbon From Eichhornia. *Journal of Chemical Technology and Biotechnology*. 77 Issue 4, 458-464.

Kraemer, E.O. (2003), "Colloids," Chapter XX "Treatise on Physical Chemistry.

Kumar U, Acharya J. (2011). Thermodynamics of the Sorption of Pb (II) from Aqueous Solution on Ncrh. *International Journal of Chemical Engineering and Applications*. 2(6). <http://ijcea.org/papers/144-A655.pdf>.

Lef (1998). Retrieved from <http://www.lef.org/protocols/prtcl-156.shtml>

Lenntech (1998). Retrieved from <http://www.lenntech.com/heavy-metals.htm>

Liu J, Liu L, Li H, Zhang H, Liu J, Zhang H. (2012). Equilibrium, Kinetic and Thermodynamic Studies of Lead (II) Bioabsorption on same leaf. *Resources*, 7(3). 3555-3572.

Liu, B., Wang, D., Yu, G. And Meng, X. (2013). Adsorption of heavy metal ions, dyes and proteins by chitosan composites and derivatives- A Review. *Journal of Ocean University of China*. 12 (3): 500-508.

Murthy RC, Pandey R, Ansaril Ng, Prasad R.I. (2014). Pb (II) Removal from aqueous solution by *Cucumis sativus* (cucumber) peel, kinetic, equilibrium and thermodynamic study, *American Journal of Environmental Protection*. 2(3):51-58.

Netzer, A and De Hughes (1984).” Adsorption of Copper, Lead, and Cobalt by Activated Carbon”. *Water Research*. 18 issue No. 8, 927-933.

Nwabanne JT, Igbokwe PK. (2012). Comparative study of lead (ii) removal from aqueous solution using different adsorbents. *International Journal of Engineering Research and Applications* (IJERA). 2 (4): 1830-1838.

Nwafor, J.C., (2006). Environmental Impact Assessment for Sustainable Development: The Nigerian Perspective; Environment and Development Policy Centre for Africa, Enugu.

Omar W, Itawi H. A. (2007) Removal of Pb²⁺ Ions from Aqueous Solutions by Adsorption on Kaolinite clay. *American Journal of Applied Sciences*. 4(7). 234-238.

Peter,M.,Gopalakrishnan,S. and Kannadasan, T.(2013) Adsorption of Copper by Ethylenediamine-modified cross-linked Magnetic Chitosan Resin (EMCMCR). *American Journal of Engineering Research*. 5:114-121.

Qinn, Y., Cai, L., Feng, D., Shi, B., Liu, J., Zhang, W. and Shen, Y. (2007). Combined use of Chitosan and Alginate in the treatment of wastewater. *Journal of Applied Polymer Science*. 104:3581–3587.

Reiad, N. A., Abdelsalam, O. E., Abadir, E. F. and Harraz, F. A. (2013). Preparation, Characterization and Application of Chitosan / polyethylene glycol blend film for removal of iron from water. *International Journal of Sustainable Water and Environmental Systems*. 5(1):43-49.

This work is licensed under a [Creative Commons Attribution 4.0 Unported License](https://creativecommons.org/licenses/by/4.0/)
ISSN: 1597 – 9928 Science and Education Development Inst., Nigeria

Rejinolda S, Naira A, Sabithaa M, Chennazhia K.P, Tamurab H., Naira S.V., Jayakumar R. (2012) Synthesis, Characterization and in Vitro Cytocompatibility Studies of Chitin Nanogels for Biomedical Applications, *Carbohydrate Polymers*, (87) 943– 949.

Repo, E., Warchol, J. K., Bhatnagar, A. and Sillanpää, M. (2011). Heavy Metals Adsorption by Novel EDTA-modified Chitosan – Silica Hybrid Materials. *J. Colloid Interface Sci.* 358(1):261-267.

Seniunait J, Vaiskunait R, Bolutien, Vilnius and Lithuania (2014). Coffee Grounds as an Adsorbent for Copper and Lead removal from aqueous solutions, The 9th International Conference Environmental Engineering, 22-23.

Shanmugapriya, A., Hemalatha, M., Scholastica, B., Arul, A. And Prasad, T. (2013). Adsorption studies of Lead (II) and Nickel (II) ions on Chitosan-g-polyacrylonitrile. *Derpharma Chemical*. 5(3):141-155.

Shanmugapriya, A., Ramya, R., Ramasubramaniam, S. and Sudha, P. N., Nadu, T. (2011). Studies on removal of Cr (VI) and Cu (II) ions using chitosan. *Archives of Applied Science Research* 3(3):424-435.

Sharma, B.K., (2002). Engineering Chemistry. Krishna Prakashan Media PVT. Ltd., Meerut-India.

Yadava SK, Sinhab S., Singha DK, (2013). Removal of lead (II) from aqueous solution using papaya seed carbon characteristics and kinetics study. *International Journal of Chemical and Environmental Engineering* 4(2).
<http://citeseerx.ist.psu.edu/viewdoc/download;jsessionid=207C26A92739F322C8C7FA0E0B0221AF?doi=10.1.1.677.5645&rep=rep1&type=pdf>

Smith, Edward (1998). Surface Complexation Modeling of Metal removal by Recycled Iron sorbent. *Journal of Environmental Engineering*. 124, 913-920.

Smith, Edward, and Afshin Amini (2000). Lead removal in fixed beds by recycled iron Material. *Journal of Environmental Engineering* 126 no.1, 58-65.

Soundarrajan, M., Gomathi, T. And Sudha, P. N. (2013). Understanding the adsorption efficiency of chitosan coated carbon on heavy metal removal. *International Journal of Scientific and Research Publication*. 3(1):1-10.

This work is licensed under a [Creative Commons Attribution 4.0 Unported License](#)
ISSN: 1597 - 9928 Science and Education Development Inst., Nigeria

Singh D, Sujatal K, Mishra Ak, Upadhyay M, Saroj K. July, (2014). Red mud as adsorbent to removal lead (II) from aqueous solutions, *Research Journal of Recent Sciences*. 3(7):18-27.

Thilagan, J., Gopalakrishnan, S., And Kannadasan, T. (2013). (a) Cellulose and cross linked by formaldehyde,(b) chitosan immobilised on red soil,(c) chitosan reinforced by banana stem. *Journal of Engineering Technology*. 3(1):35-60.

Trivedi N, Pandhare GG, Rajesh Pathrabe R, Dawande SD (2013). Adsorption of Cadmium (II) and Lead (II) from a stock solution using neem leaves powder as a low-cost adsorbent. *International Journal of Innovative Research in Science, Engineering and Technology*. 2(10): 345-350.

Tumin Nd, Luqman Ac, Zawani Z, Suraya Ar (2008). Adsorption of copper from aqueous solution by *Elais guineensis* Kernel Activated Carbon. *J. Eng. Sci. Tech*. 3(2):180-189.

Vernon L. Snoeyink, Walter J. Weber Jr. (1967). The surface chemistry of active carbon. *Environmental Science Technology*. 1 (3): 228-234.

Wan Ngah, W. S., Teong, L. C., Toh, R. H. and Hanafiah, M. A. K. M. (2012) Utilization of chitosan-zeolite composite in the removal of Cu (II) from aqueous solution: Adsorption, desorption and fixed bed column studies. *Chemical Engineering Journal*. 209; 46–53.

Wan, W. S., Teong, N. L.C. and Hanafiah, M. A. K. M. (2011). Adsorption of dyes and Heavy Metals ions by Chitosan Composites: *A Review of Carbohydrate Polymer* 84(4): 1446-1456.

Wang, W., Huang, D., Kang, Y. and Wang, A. (2013). Biointerfaces One-step in situ fabrication of a granular semi-IPN hydrogel based on chitosan and gelatin for fast and efficient adsorption of Cu^{2+} ion. *Colloids and Surfaces B* :106:51-59.

Wu, F. C., Tseng, R. L. and Juang, R. S. (2001). Enhanced abilities of highly swollen chitosan beads for color removal and tyrosinase immobilization. *Journal of Hazardous Material*. 81(1-2):167-177.

Yavuz O, Guzel R, Aydin F, Tegin I, Ziyadanogullari R. 2006. Removal of cadmium and lead from aqueous solution by calcite, *Polish Journal of Environ. Stud.* 16(3): 236-290.

Zahra Naseem (2012). Lead Removal from water by low cost adsorbents, a-review, *Pak. J. Anal Environ Chem.*; 13(1):01-08.

Zuo, X. (2014). Preparation and Evaluation of Novel Thiourea/Chitosan Composite Beads for Copper (II) Removal in Aqueous Solutions. *Industrial Engineering Chemistry Research* 53: 1249–1255.